




PN# 11003011025



Shieldex® Bern

- Purpose: Conductive non-woven fabric for general use.
- Description: Silver (Ag) plated non-woven Cerex® fabric.
- Raw material: Cerex® 0.25—0.30 oz sq/yd nylon non-woven fabric.
- Surface Resistivity: < 1.0 Ohms / □
- RF Shielding Effectiveness: Average > 40 dB from 30MHz to 10GHz
- Temperature Range: -40°C to 100°C / -40°F to 212°F
- Total Thickness: 0.0035" (0.09mm) ± 25%
- Number of Splices: 1/100 Lm nominal
- Weight: 10-16 g/m²
- Roll Widths: 39" ± 1" (100cm)
- Master Roll Lengths: Average 100 Lm / 109 Lyd



PRODUCT APPLICATION EXAMPLES

- ⇒ Base material for composite shielding products
- ⇒ Base material for EMI/RFI garments
- ⇒ Passive static eliminator for copier, fax & printers
- ⇒ EMI/RFI cable shielding
- ⇒ Conductive fabric tape

The above information has been compiled from our manufacturing area according to the latest state of development and application technology. Since application and further processing are beyond our control, no liability of the producer can be derived from the contents of this application guide. All deviant or transcending data sheet information must be confirmed in written form by the manufacturer. Our general terms and conditions apply in all cases. All previous data sheets are invalid with the publication of this data sheet.

Accreditations:
RoHS: Compliant
Reach: Compliant
Acc. ISO 9001:2015

V Technical Textiles, Inc
 4502 State Rt. 31
 Palmyra, NY 14522
 Phone: 315-597-1674
 Fax: 315-597-6687
 Web: www.vtechtextiles.com
 Email: info@vtechtextiles.com



Statex Produktions
 -und Vertriebs GmbH
 Kleiner Ort 11 28357
 Bremen Germany
 Tel: +49 421 27 50 47
 Fax: +49 421 27 36 43
 info@statex.de